Sales Specifications Rev. 5, August 2010

Description

Composition	Powdered polyolefin processing additive containing fluoropolymer, dusting agent, and lubricant
Form	Free-flowing powder
Color	Homogeneous white to pale amber

Requirements

Property	Limits	Test Method
Particle Size, % retained on		ASTM D1921
U.S. Std. #16 Screen	2.0 max.	
U.S. Std #80 Screen	50 min.	
Volatiles, wt%	1.5 max.	V510.9000 or DW-Viton [™] -038
Flow rate, sec	40 max.	ASTM D1895
Bulk Density, g/cc	0.66-0.86	ASTM D1895
Fluoropolymer, wt%	51.7-53.7	Mass Balance
Fluorine, wt%	33.8-35.2	Mass Balance
Polyethylene glycol, wt%	41.1-43.1	Mass Balance

For more information, visit Viton.com

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

© 2016 The Chemours Company FC, LLC. Viton*, FreeFlow*, and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours* and the Chemours Logo are trademarks of The Chemours Company.

Replaces: VFE-A10065-00-F0810

C-10960 (8/16)

